



Latex PF Sterile Examination Polymer Coated Powder Free Natural Rubber Latex Examination Glove

Benefits

- Sterile
- Ambidextrous
- Good dry and wet grip
- Packed in Thermoform film pouch
- Fully textured

Features

- Low protein content 20-25µg/dm²
- Sterilized by Gamma Irradiation
- AQL 1.5
- Product is tested according to ASTM & EN testing methods for examination gloves and meet ASTM D3578 & EN 455 Part 1&2 international standard requirements

Powder Free: yes **Surface:** Textured **Cuff:** Beaded

Colors:



Size	Palm Width (mm)	Length (mm)
Extra Small	76-79	Min. 240
Small	83-85	Min. 240
Medium	94-96	Min. 240
Large	104-106	Min. 240
Extra Large	115-117	Min. 240

Physical Properties	Before ageing	After ageing	Glove Thickness (Single Wall/mm)
Tensile Strength	21-23 MPa	19-22 MPa	Cuff 0.10-0.11
Elongation at break	740-820%	690-800%	Palm 0.14-0.15
Force at break	9.5-10.0 N	8.5-9.0 N	Finger 0.16-0.17

Inspection Parameter	Defect Description	Inspection Plan	Level	AQL
Dimension	Glove Thickness (Cuff, Palm, Fingers, Width, Length)		S-2	4.0
Physical Properties	Tensile Strength, Ultimate Elongation Force at Brake		S-2	4.0
Visual Inspection	Major Defect, Minor defects		G-1	2.5, 4.0
1000 ml Water Tight Test	Holes, Leaks		G-1	1.5
Powder Free Residue	Powder residue content		N = 5	
Protein	Protein Content		N = 3	

Packing Description

Packing	1 pair per pouch, 50 pouches per dispenser, 6 dispenser per carton, 300 pairs per Carton
Lot Number Structure	(YYYY = Year of manufacturing, XXX = Julian Day)
Recommended Shelf Life	3 Years upon manufacturing date