

Latex Powder Free High Risk

Powder Free Natural Rubber Latex Examination Glove



Benefits

- Extra-long, extended cuff
- Extra-thick (13Mil) for maximum security
- Ambidextrous
- Excellent durability
- Essential in vigorous handling during emergency situations

Features

- Low protein content 20-30µg/dm²
- AQL 1.5
- Product is tested according to ASTM & EN testing methods for examination gloves and meet ASTM D3578 & EN 455 1-4, EN374 (CAT III, Type B), EN1186 international standard requirements

Powder Free: yes **Surface:** Textured **Cuff:** Beaded

Colors:



Size	Palm Width (mm)	Length (mm)
Small	85 +/-5	Min. 300
Medium	95 +/-5	Min. 300
Large	106 +/-5	Min. 300
Extra Large	116 +/-5	Min. 300
Extra Extra Large	125 +/-5	Min. 300

Physical Properties	Before ageing	After ageing	Glove Thickness (Single Wall/mm)	
			Cuff	Palm
Tensile Strength	Min. 18 MPa	Min. 14 MPa	Min. 0.25	Min. 0.32
Elongation at break	Min. 650%	Min. 500%	Min. 0.33	
Force at break	Min. 6 N	Min. 6 N		

Inspection Parameter	Defect Description	Inspection Plan	Level	AQL
Dimension	Glove Thickness (Cuff, Palm, Fingers, Width, Length)		S-2	4.0
Physical Properties	Tensile Strength, Ultimate Elongation Force at Brake		S-2	4.0
Visual Inspection	Major Defect, Minor defects		G-1	2.5, 4.0
1000 ml Water Tight Test	Holes, Leaks		G-1	1.5
Powder Free Residue	Powder residue content		N = 5	
Protein	Protein Content		N = 3	

Packing Description

Packing	100 pieces per Dispenser, 10 x 100 pieces per Carton
Lot Number Structure	(YYYY = Year of manufacturing, XXX = Julian Day)
Recommended Shelf Life	3 Years upon manufacturing date