

# Nitrile Powder Free 300mm - 6 mil

## Powder Free Nitrile High Risk Glove



### Benefits

- Silky comfort fitting
- Soft & light
- Elastic & yields to hand
- Superior puncture resistance
- Fit with wet & dry grip
- Fingertips textured

### Features

- AQL 1.5
- Product is tested according to ASTM testing methods for examination gloves and meet ASTM D6319 & EN 455 1:3, EN374 (CAT III, Type B), EN1186 international standard requirements

Powder Free: yes    Surface: Textured    Cuff: Beaded

Colors:



Size	Palm Width (mm)	Length (mm)
Small	85 +/- 5	Min. 295
Medium	95 +/- 5	Min. 295
Large	106 +/- 5	Min. 295
XLarge	116 +/- 5	Min. 295
XXLarge	125 +/- 5	Min. 295

Physical Properties	Before ageing	After ageing	Glove Thickness	(Single Wall/mm)
Tensile Strength	Min. 18 MPa	Min 14 MPa	Cuff	0.09
Elongation at break	Min. 500%	Min. 400%	Palm	0.14
Force at break	Min. 6.0 N	Min. 6.0 N	Finger	0.19

Inspection Parameter	Defect Description	Inspection Plan	Level	AQL
Dimension	Glove Thickness (Cuff, Palm, Fingers, Width, Length)		S-2	4.0
Physical Properties	Tensile Strength, Ultimate Elongation Force at Brake		S-2	4.0
Visual Inspection	Major Defect, Minor defects		G-1	2.5, 4.0
1000 ml Water Tight Test	Holes, Leaks		G-1	1.5
Powder Free Residue	Powder residue content		N = 5	

### Packing Description

Packing	50 pieces per Dispenser, 10 x 100 pieces per Carton
Lot Number Structure	(YYYY = Year of manufacturing, XXX = Julian Day)
Recommended Shelf Life	3 Years upon manufacturing date