



# Nitrile Accelerator Free 6.0g

## Powder Free Single Chlorinated Nitrile Examination Glove

### Benefits

- Formulated without Chemical Accelerators and Sulphur
- LOW DERMA Patent
- Protect Against Glove Induced Type I & Type IV Hypersensitivities and Blood-borne Pathogens & Viruses
- Protection against accidental Fentanyl poisoning

### Features

- AQL 1.5
- Product is tested according to ASTM testing methods for examination gloves and meet ASTM D6319 & EN 455 1/2/3, EN374 (CAT III, Type B), EN1186 international standard requirements

**Powder Free:** yes    **Surface:** Textured    **Cuff:** Beaded

**Colors:**



Size	Palm Width (mm)	Length (mm)
Extra Small	75 +/-5	Min. 240
Small	85 +/-5	Min. 240
Medium	95 +/-5	Min. 240
Large	106 +/-5	Min. 240
Extra Large	116 +/-5	Min. 240
Extra Extra Large	125 +/-5	Min. 240

Physical Properties	Before ageing	After ageing	Glove Thickness (Single Wall/mm)
Tensile Strength	Min. 18 MPa	Min. 14 MPa	Cuff Min. 0.08
Elongation at break	Min. 500%	Min. 400%	Palm Min. 0.12
Force at break	Min. 6.0 N	Min. 6.0 N	Finger Min. 0.15

Inspection Parameter	Defect Description	Inspection Plan	Level	AQL
Dimension	Glove Thickness (Cuff, Palm, Fingers, Width, Length)		S-2	4.0
Physical Properties	Tensile Strength, Ultimate Elongation Force at Brake		S-2	4.0
Visual Inspection	Major Defect, Minor defects		G-1	2.5, 4.0
1000 ml Water Tight Test	Holes, Leaks		G-1	1.5
Powder Free Residue	Powder residue content		N = 5	

### Packing Description

Packing	100 pieces per Dispenser, 10 x Dispenser per Carton
Lot Number Structure	(YYYY = Year of manufacturing, XXX = Julian Day)
Recommended Shelf Life	3 Years upon manufacturing date