



## Diamond Nitrile Accelerator Free 8.5g Powder Free Nitrile Examination Glove

### Benefits

- Formulated without Chemical Accelerators and Sulphur
- LOW DERMA Patent
- Extreme Grip (dry & wet)
- High Comfort & Durability
- Excellent Resistance against Viruses, Bacteria and Chemicals (JKPT)

### Features

- AQL 1.5
- Product is tested according to ASTM testing methods for examination gloves and meet ASTM D6319 & EN 455, EN374 (CAT III, Type B, JKPT), PPE Module B & C2, EN421, EN1186 international standard requirements

**Powder Free:** yes

**Surface:** Diamond Grip

**Cuff:** Beaded

**Colors:**



Size	Palm Width (mm)	Length (mm)
Small	85 +/-5	Min. 240
Medium	95 +/-5	Min. 240
Large	106 +/-5	Min. 240
Extra Large	116 +/-5	Min. 240
Extra Extra Large	125 +/-5	Min. 240

Physical Properties	Before ageing	After ageing	Glove Thickness (Single Wall/mm)
Tensile Strength	Min. 18 MPa	Min. 14 MPa	Cuff Min. 0.09
Elongation at break	Min. 500%	Min. 400%	Palm Min. 0.16
Force at break	Min. 6.0 N	Min. 6.0 N	Finger Min. 0.18

Inspection Parameter	Defect Description	Inspection Plan	Level	AQL
Dimension	Glove Thickness (Cuff, Palm, Fingers, Width, Length)		S-2	4.0
Physical Properties	Tensile Strength, Ultimate Elongation Force at Brake		S-2	4.0
Visual Inspection	Major Defect, Minor defects		G-1	2.5, 4.0
1000 ml Water Tight Test	Holes, Leaks		G-1	1.5
Powder Free Residue	Powder residue content		N = 5	

### Packing Description

Packing	100 pieces per Dispenser, 10 x Dispenser per Carton
Lot Number Structure	(YYYY = Year of manufacturing, XXX = Julian Day)
Recommended Shelf Life	3 Years upon manufacturing date